

Spec Bond


3015 W. Cornelia Ave. Chicago, IL 60018 Phone: 773-967-0138 Fax: 312-268-5448 www.SpecBond.com

PRODUCT DATA SHEET SB500U

Description

SB500U is a 0.005" thick acrylic pressure sensitive adhesive in film form (transfer film) supported with random dispersed glass fibers. The adhesive is very high in tack and peel adhesion. **SB500U** exhibits excellent low temperature properties and is intended for bonding to difficult surfaces including many low energy surfaces. The product is self-wound on a 76 lb poly coated release paper.

Construction



Feature and Benefits

- Very high peel and tack
- · Excellent low temperature properties
- Bonds well to many low energy substrates

Typical Properties (not to be used for specification purposes)

- J b			
PROPERTY	TEST METHOD	VALUE (US)	VALUE (METRIC)
Adhesive Thickness	PSTC-133	0.005 inches	0.127 mm
Max. Service Temp.		175°F Continuous	79°C Continuous
		225°F Intermittent	107°C intermittent
Peel Adhesion	PSTC-101	129 oz/inch	36.2 N /25 mm
Loop Tack	PSTC-16	115 oz/inch ²	4.91 N/cm ²
Shear Adhesion	PSTC-107	>24 hr. @ 2.2 psi	>24 hr. @ 1.5 N/cm ²

For maximum adhesion, bonding surfaces should be clean, dry and free from grease and oils. The firmer the application pressure and the greater the contact area, the stronger the bond.

IMPORTANT NOTICE TO PURCHASER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his or her intended use, and the user assumes all risk and liability whatsoever in connection therewith. No representative of ours has authority to waive or change the foregoing provisions, but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to the needs and circumstances prevailing in their business.